

TRAGAL

Water absorption at atmospheric pressure (EN13755)	0,30%
Compressive resistance (MPa) (EN1926)	165
Resistance to bending stress (MPa) (EN12372)	15,9
Frost resistance (48 cycles) (change in apparent volume) (EN12371).....	—
Frost resistance (56 cycles) (change in apparent volume) (EN12371).....	6,9
Abrasion resistance (mm) (EN14157)	15,4
Anchor breaking load (N) (EN13364)	2250
Thermal Shock (change in mass) (EN14066).....	-0,02% (does not change)
Apparent density (Kg/m ³) (EN1936).....	2640
Open porosity (EN1936)	1,00%

* Given that granite is a natural product, the technical characteristics presented may vary slightly. We are prepared to answer any questions about the characteristics of our materials. All our testing is carried out in accordance with current European Union norms.

